




collezione cesaro

ANTARA

  		
Composition	Surface	100% Polyurethaan
Width		140 cm ± 2%
Weight		820 g/ml
Thickness		1,10 mm
Color Fastness		4
Breaking Resistance		ISO 13.94-1 N/5 cm > 170
Breaking elongation	Weft Warp	30% 50%
Tear strenght	Weft Warp	100 N/cm 90 N/cm
Flex Bally (UNE 53243-20)		100.000 cycles
Abrasion	MARTINDALE	>200.000 cycles
Heat resistance		150°
Fire Retardant treatment	UNE 1021 part 1 and 2 BS 5852 parts 1 and 2 IMO A652	YES YES YES
Water vapour permeability		500 g/m2/24H

Collezione Cesaro
Venbroekstraat 5 5253 AS Nieuwkuyk
The Netherlands
T 0031(0)73 5117846
F 0031(0)73 5116829
E info@collezionecesaro.com